



PTS- Creamid A3H7G12.2S*9217

Teknor Apex Company (Chem Polymer) - Polyamide 66 + PA 6I/6T

General Information

General

Material Status	• Preliminary Data			
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America	
Forms	• Pellets			

ASTM & ISO Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.73	1.73	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.40	0.40	%	
Flow	0.20	0.20	%	
Water Absorption (24 hr, 73°F)	0.30	0.30	%	ISO 62
Water Absorption				ISO 62
Saturation, 73°F	2.3	2.3	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	3.05E+6	2.90E+6	psi	ISO 527-2
Tensile Stress (Break)	37700	34100	psi	ISO 527-2
Tensile Strain (Break)	3.0	3.0	%	ISO 527-2
Flexural Modulus (73°F)	2.47E+6	2.32E+6	psi	ISO 178
Flexural Stress	50800	50000	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
73°F	6.2	6.2	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179
-22°F	33	33	ft·lb/in ²	
73°F	33	33	ft·lb/in ²	
Notched Izod Impact Strength				ISO 180
73°F	6.2	6.2	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				ISO 75-2/B
66 psi, Unannealed	491	491	°F	
Heat Deflection Temperature				ISO 75-2/A
264 psi, Unannealed	401	401	°F	
Vicat Softening Temperature				
--	482	482	°F	ISO 306/A
--	473	473	°F	ISO 306/B
Melting Temperature	509	509	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.031 in	HB	--		
0.06 in	HB	--		
0.13 in	HB	--		

PTS- Creamid A3H7G12.2S*9217

Teknor Apex Company (Chem Polymer) - Polyamide 66 + PA 6I/6T

Processing Information		
Injection	Dry	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 4.0	hr
Nozzle Temperature	554	°F
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	176 to 230	°F

Notes

¹ Typical properties: these are not to be construed as specifications.