



Chemlon® 833 GH

Teknor Apex Company - Polyamide 6/12 Copolymer

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.33	g/cm ³	ISO 1183
Molding Shrinkage	0.15 to 0.35	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	23900	psi	ISO 527
Tensile Strain (Break)	4.0	%	ISO 527
Flexural Modulus	1.20E+6	psi	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (73°F)	5.7	ft·lb/in ²	ISO 180/A
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	423	°F	ISO 11357

Notes

¹ Typical properties: these are not to be construed as specifications.