+135-3858-6433 (GuangDong) +188-1699-6168 (ShangHai) +852-6957-5415 (HongKong)



# Sinpolene MBW0722

## Teknor Apex Asia Pacific PTE. LTD. - Polyethylene

### **General Information**

#### **Product Description**

Sinpolene MBW0722 is a polyethylene-based white masterbatch designed specifically for use in tubular film blowing, blow moulding and extrusion of polyolefins. With its high pigment loading, Sinpolene MBW0722 offers high colouring value with excellent quality and performance.

The blue undertone of this masterbatch is attributed by specially selected high performance, fine crystal size rutile titanium dioxide.

Sinpolene MBW0722 is delivered as free flowing pellets for processing convenience.

#### **CHARACTERISTICS**

- \* Easy processing
- \* Good dispersion
- \* High opacifying power
- \* Excellent whiteness

Commercial: Active			
Asia Pacific			
<ul> <li>Titanium Dioxide Equiv</li> </ul>	alent, 50% Filler by Weight		
<ul> <li>General Purpose</li> </ul>			
• Film	<ul> <li>Masterbatch</li> </ul>	• Sheet	
<ul> <li>RoHS Compliant</li> </ul>			
• White			
• Pellets			
Blown Film	<ul> <li>Sheet Extrusion</li> </ul>		
	<ul> <li>Asia Pacific</li> <li>Titanium Dioxide Equiv</li> <li>General Purpose</li> <li>Film</li> <li>RoHS Compliant</li> <li>White</li> <li>Pellets</li> </ul>	Asia Pacific     Titanium Dioxide Equivalent, 50% Filler by Weight     General Purpose     Film	Asia Pacific     Titanium Dioxide Equivalent, 50% Filler by Weight     General Purpose     Film

ASTM & ISO Properties <sup>1</sup>			
Physical	Nominal Value Unit	Test Method	
Density / Specific Gravity	2.06	ASTM D792	
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10 to 30 g/10 min	ASTM D1238	
Moisture Content	< 0.20 %	ASTM D3030	

Recommended dosage: 5 - 10%

#### **Notes**

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.