



Sinpolene TPP2020M

Teknor Apex Asia Pacific PTE. LTD. - Polypropylene Copolymer

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Filler / Reinforcement	• Talc, 20% Filler by Weight
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.06		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	16	g/10 min	ASTM D1238
Molding Shrinkage - Flow	9.0E-3 to 0.012	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	4060	psi	ASTM D638
Tensile Elongation (Break)	50	%	ASTM D638
Flexural Modulus	254000	psi	ASTM D790
Flexural Strength	6380	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.64	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	237	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.