



Flexalloy® 9600-72

Teknor Apex Company - Polyvinyl Chloride Elastomer

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant • High Heat Resistance	• Low Temperature Flexibility • Sunlight Resistant (720 hours)	
Uses	• Cable Jacketing		
Wire Types	• SEOW • SEW	• SJEOW • SJEW	• STEOW • STEW
Agency Ratings	• UL Class 11 • UL Class 12	• UL Class 36 • UL Class 43	• UL QMTT2
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2100	psi	ASTM D638
Tensile Elongation (Break)	330	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	72		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-63.4	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	6.19		
1 MHz	3.91		
Dissipation Factor			ASTM D150
1 kHz	0.076		
1 MHz	0.11		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	26	%	ASTM D2863

Notes

¹ Typical properties: these are not to be construed as specifications.