



Monprene® SP-16238D NAT

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Monprene SP-16238D NAT is a general purpose thermoplastic elastomer designed for a variety of consumer product applications. Monprene SP-16238D NAT is a high hardness, low density grade thermoplastic elastomer suitable for both injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Medium Flow	• Medium Hardness	
Uses	• Consumer Applications	• Sporting Goods	
RoHS Compliance	• RoHS Compliant		
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.892		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	4.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1160	psi	ASTM D412
Tensile Strength (Break)	3480	psi	ASTM D412
Tensile Elongation (Break)	600	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore D, 1 sec, Injection Molded	38		
Shore D, 5 sec, Injection Molded	35		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	380 to 420	°F
Middle Temperature	380 to 420	°F
Front Temperature	380 to 420	°F
Nozzle Temperature	380 to 420	°F
Processing (Melt) Temp	380 to 420	°F
Mold Temperature	60 to 90	°F
Injection Pressure	200 to 800	psi
Injection Rate	Fast	
Back Pressure	25.0 to 100	psi

Monprene® SP-16238D NAT

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	360 to 400	°F
Cylinder Zone 2 Temp.	360 to 400	°F
Cylinder Zone 3 Temp.	360 to 400	°F
Cylinder Zone 4 Temp.	360 to 400	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	360 to 400	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.