



# Sarlink® TPE ML-1130B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

## General Information

### Product Description

Sarlink ML-1100 is a general purpose thermoplastic elastomer series, available in NAT and BLK designed for automotive interior applications. Sarlink ML-1130B BLK is a low hardness, high density, filled, UV stabilized grade suitable for injection molding.

### General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Flexibility • Good Moldability	• Good Tear Strength • Good Toughness • High Density • High Specific Gravity • Low Flow	• Low Hardness • Resilient • Sunlight Resistant • UV Resistant • Weather Resistant
Uses	• Automotive Applications • Automotive Interior Parts • Flexible Grips	• General Purpose • Grommets • Knobs	• Rubber Replacement • Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.50	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress <sup>2</sup>			ISO 37
Across Flow : 100% Strain	79.8	psi	
Flow : 100% Strain	146	psi	
Tensile Stress <sup>2</sup>			ISO 37
Across Flow : Break	479	psi	
Flow : Break	305	psi	
Tensile Elongation <sup>2</sup>			ISO 37
Across Flow : Break	860	%	
Flow : Break	470	%	
Tear Strength <sup>3</sup>			ISO 34-1
Across Flow	70	lbf/in	
Flow	93	lbf/in	
Compression Set <sup>4</sup>			ISO 815
73°F, 22 hr	15	%	
158°F, 22 hr	39	%	
194°F, 70 hr	71	%	
257°F, 70 hr	94	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 1 sec, Injection Molded	32		
Shore A, 5 sec, Injection Molded	30		
Shore A, 15 sec, Injection Molded	28		

## Sarlink® TPE ML-1130B BLK (PRELIMINARY DATA)

### Teknor Apex Company - Thermoplastic Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air <sup>5</sup>			ISO 188
Across Flow : 230°F, 1008 hr	70	%	
Flow : 230°F, 1008 hr	120	%	
Across Flow : 100% Strain 230°F, 1008 hr	-1.8	%	
Flow : 100% Strain 230°F, 1008 hr	-16	%	
Across Flow : 257°F, 168 hr	73	%	
Flow : 257°F, 168 hr	130	%	
Across Flow : 100% Strain 257°F, 168 hr	-7.3	%	
Flow : 100% Strain 257°F, 168 hr	-20	%	
Change in Tensile Strain at Break in Air <sup>5</sup>			ISO 188
Across Flow : 230°F, 1008 hr	23	%	
Flow : 230°F, 1008 hr	99	%	
Across Flow : 257°F, 168 hr	45	%	
Flow : 257°F, 168 hr	110	%	
Change in Shore Hardness in Air			ISO 188
Shore A, 230°F, 1008 hr <sup>6</sup>	-2.2		
Shore A, 230°F, 1008 hr	-2.1		
Shore A, 230°F, 1008 hr <sup>7</sup>	-3.6		
Shore A, 257°F, 168 hr <sup>8</sup>	-2.9		
Shore A, 257°F, 168 hr <sup>6</sup>	-3.2		
Shore A, 257°F, 168 hr <sup>7</sup>	-3.5		
<b>Fill Analysis</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Apparent Viscosity (392°F, 206 sec <sup>-1</sup> )	177	Pa·s	ASTM D3835
<b>Additional Information</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Xenon Weatherometer			SAE J1885
For BLK grade only: Delta E - 1250 kJ	0.380		
For BLK grade only: Delta E - 2500 kJ	0.400		

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

# Sarlink® TPE ML-1130B BLK (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

---

### Injection Notes

---

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Type 1, 20 in/min

<sup>3</sup> Method Ba, Angle (Unnicked), 20 in/min

<sup>4</sup> Type A

<sup>5</sup> Type 1

<sup>6</sup> 5 sec

<sup>7</sup> 1 sec

<sup>8</sup> 15 sec