



Sarlink® TPE ML-1670B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Sarlink ML-1600 series is a high performance, high flow thermoplastic elastomer series, available in NAT and BLK designed for automotive interior applications. Sarlink ML-1670B BLK is a medium hardness, medium density, UV stabilized grade with excellent surface appearance suitable for injection molding.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Flexibility • Good Moldability	• Good Surface Finish • Good Tear Strength • Good Toughness • High Flow • Medium Density	• Medium Hardness • Resilient • Sunlight Resistant • UV Resistant • Weather Resistant
Uses	• Automotive Applications • Automotive Interior Parts • Flexible Grips	• Grommets • Knobs • Rubber Replacement	• Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.990	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	18	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ISO 37
Across Flow : 100% Strain	290	psi	
Flow : 100% Strain	390	psi	
Tensile Stress ²			ISO 37
Across Flow : Break	972	psi	
Flow : Break	899	psi	
Tensile Elongation ²			ISO 37
Across Flow : Break	800	%	
Flow : Break	700	%	
Tear Strength ³			ISO 34-1
Across Flow	150	lbf/in	
Flow	150	lbf/in	
Compression Set ⁴			ISO 815
73°F, 22 hr	27	%	
158°F, 22 hr	46	%	
194°F, 70 hr	68	%	
257°F, 70 hr	93	%	

Sarlink® TPE ML-1670B BLK (PRELIMINARY DATA)
Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 1 sec, Injection Molded	73		
Shore A, 5 sec, Injection Molded	70		
Shore A, 15 sec, Injection Molded	68		
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	3.3	%	
Flow : 230°F, 1008 hr	-3.6	%	
Across Flow : 100% Strain 230°F, 1008 hr	9.7	%	
Flow : 100% Strain 230°F, 1008 hr	13	%	
Across Flow : 257°F, 168 hr	9.8	%	
Flow : 257°F, 168 hr	0.0	%	
Across Flow : 100% Strain 257°F, 168 hr	5.9	%	
Flow : 100% Strain 257°F, 168 hr	10	%	
Change in Tensile Strain at Break in Air ⁵			ISO 188
Across Flow : 230°F, 1008 hr	-5.1	%	
Flow : 230°F, 1008 hr	-4.8	%	
Across Flow : 257°F, 168 hr	11	%	
Flow : 257°F, 168 hr	7.2	%	
Change in Shore Hardness in Air			ISO 188
Shore A, 230°F, 1008 hr ⁶	3.1		
Shore A, 230°F, 1008 hr ⁷	3.6		
Shore A, 230°F, 1008 hr ⁸	2.9		
Shore A, 257°F, 168 hr ⁷	3.3		
Shore A, 257°F, 168 hr ⁶	2.7		
Shore A, 257°F, 168 hr ⁸	1.8		
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	111	Pa·s	ASTM D3835
Additional Information	Nominal Value	Unit	Test Method
Xenon Weatherometer			SAE J1885
Delta E - 1250 kJ	1.30		
Delta E - 2500 kJ	1.30		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F

Sarlink® TPE ML-1670B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Injection	Nominal Value	Unit
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 1, 20 in/min

³ Method Ba, Angle (Unnicked), 20 in/min

⁴ Type A

⁵ Type 1

⁶ 5 sec

⁷ 15 sec

⁸ 1 sec