



# Sarlink® TPE EE-2260B (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

## General Information

### Product Description

The Sarlink EE-2200 Series is a general purpose thermoplastic elastomer series, available in BLK, designed for automotive exterior extrusion applications. Sarlink EE-2260B is a medium hardness, high density, UV stabilized grade with very good extrudability.

### General

|                   |  |   |  |
|-------------------|--|---|--|
| Material Status   | • Preliminary Data   |   |  |
| Availability      | • Africa & Middle East<br>• Asia Pacific                       | • Europe<br>• Latin America                                   | • North America  |
| Additive          | • UV Stabilizer  |   |  |
| Features          | • Good Adhesion<br>• Good Flexibility<br>• Good Processability | • Good Toughness<br>• High Density<br>• High Specific Gravity | • Medium Hardness<br>• Ozone Resistant<br>• UV Resistant |
| Uses              | • Automotive Applications<br>• Automotive Exterior Parts       | • Automotive Exterior Trim<br>• Rubber Replacement            |  |
| RoHS Compliance   | • RoHS Compliant   |   |  |
| Appearance        | • Black  |   |  |
| Forms             | • Pellets  |   |  |
| Processing Method | • Extrusion  |   |  |

## ASTM & ISO Properties <sup>1</sup>

| Physical   | Nominal Value | Unit              | Test Method |
|--|---------------|-------------------|-------------|
| Density  | 1.18          | g/cm <sup>3</sup> | ISO 1183    |
| Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)          | 0.50          | g/10 min          | ASTM D1238  |
| Elastomers   | Nominal Value | Unit              | Test Method |
| Tensile Stress                                     |               |                   | ISO 37      |
| Across Flow : 100% Strain                          | 232           | psi               |             |
| Flow : 100% Strain                                 | 319           | psi               |             |
| Tensile Stress                                     |               |                   | ISO 37      |
| Across Flow : Break                                | 1320          | psi               |             |
| Flow : Break                                       | 783           | psi               |             |
| Tensile Elongation                                 |               |                   | ISO 37      |
| Across Flow : Break                                | 790           | %                 |             |
| Flow : Break                                       | 650           | %                 |             |
| Tear Strength - Across Flow                        | 170           | lbf/in            | ISO 34-1    |
| Compression Set                                    |               |                   | ISO 815     |
| 73°F, 22 hr  | 20            | %                 |             |
| 158°F, 22 hr                                       | 31            | %                 |             |
| 257°F, 70 hr                                       | 77            | %                 |             |
| Hardness   | Nominal Value | Unit              | Test Method |
| Shore Hardness                                     |               |                   | ISO 868     |
| Shore A  | 63            |                   |             |
| Shore A, 15 sec                                    | 60            |                   |             |
| Fill Analysis                                      | Nominal Value | Unit              | Test Method |
| Apparent Viscosity (392°F, 206 sec <sup>-1</sup> ) | 266           | Pa·s              | ASTM D3835  |

# Sarlink® TPE EE-2260B (PRELIMINARY DATA)

## Teknor Apex Company - Thermoplastic Elastomer

---

### Processing Information

---

| Extrusion             | Nominal Value | Unit |
|-----------------------|---------------|------|
| Cylinder Zone 1 Temp. | 380 to 400    | °F   |
| Cylinder Zone 2 Temp. | 390 to 410    | °F   |
| Cylinder Zone 3 Temp. | 400 to 420    | °F   |
| Cylinder Zone 4 Temp. | 410 to 430    | °F   |
| Cylinder Zone 5 Temp. | 410 to 430    | °F   |
| Die Temperature       | 420 to 440    | °F   |

---

### Extrusion Notes

Screw Speed: 30 to 100 rpm

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.