



Sarlink® TPE ML-1155B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Sarlink ML-1100 is a general purpose thermoplastic elastomer series, available in NAT and BLK designed for automotive interior applications. Sarlink ML-1155B BLK is a low hardness, high density, filled grade suitable for injection molding.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Flexibility	• Good Moldability • Good Tear Strength • Good Toughness • High Density	• High Specific Gravity • Low Flow • Low Hardness • Resilient
Uses	• Automotive Applications • Automotive Interior Parts • Flexible Grips	• General Purpose • Grommets • Knobs	• Rubber Replacement • Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ISO 37
Across Flow : 100% Strain	183	psi	
Flow : 100% Strain	218	psi	
Tensile Stress ²			ISO 37
Across Flow : Break	943	psi	
Flow : Break	769	psi	
Tensile Elongation ²			ISO 37
Across Flow : Break	880	%	
Flow : Break	830	%	
Tear Strength ³			ISO 34-1
Across Flow	114	lbf/in	
Flow	126	lbf/in	
Compression Set ⁴			ISO 815
73°F, 72 hr	14	%	
158°F, 22 hr	32	%	
212°F, 22 hr	69	%	
248°F, 22 hr	78	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, Instant, Injection Molded)	52		ISO 868

Sarlink® TPE ML-1155B BLK (PRELIMINARY DATA)

Teknor Apex Company - Thermoplastic Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁵			ISO 188
Across Flow : 248°F, 1000 hr	15	%	
Flow : 248°F, 1000 hr	26	%	
Across Flow : 100% Strain 248°F, 1000 hr	14	%	
Flow : 100% Strain 248°F, 1000 hr	13	%	
Change in Tensile Strain at Break in Air ⁵			ISO 188
Across Flow : 248°F, 1000 hr	-0.10	%	
Flow : 248°F, 1000 hr	16	%	
Change in Shore Hardness in Air ⁶			ISO 188
Shore A, 248°F, 1000 hr	4.4		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 400	°F
Middle Temperature	380 to 440	°F
Front Temperature	400 to 460	°F
Nozzle Temperature	400 to 460	°F
Processing (Melt) Temp	400 to 460	°F
Mold Temperature	70 to 100	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type 2, 20 in/min

³ Method Ba, Angle (Unnicked), 20 in/min

⁴ Type A

⁵ Type 2

⁶ Instant