+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

TEKNOR APEX

Sarlink® TPE ML-1675B BLK

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Sarlink ML-1600 is a general purpose thermoplastic elastomer series, available in NAT and BLK designed for automotive interior applications. Sarlink ML-1675B BLK is a medium hardness, low density grade suitable for injection molding.

General

Material Status	• Preliminary Data		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Filled • Good Adhesion • Good Flexibility	• Good Moldability • Good Tear Strength • Good Toughness • Low Specific Gravity	• Medium Hardness • Resilient
Uses	• Automotive Applications • Automotive Interior Parts • Flexible Grips	• General Purpose • Grommets • Knobs	• Rubber Replacement • Soft Touch Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties [1]

Physical	Nominal Value	Unit	Test Method
Density	0.985	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	16	g/10 min	ASTM D1238
Elastomers	**Nominal Value**	**Unit**	**Test Method**
Tensile Stress [2]			ISO 37
Across Flow : 100% Strain	450	psi	
Flow : 100% Strain	363	psi	
Tensile Stress [2]			ISO 37
Across Flow : Break	1040	psi	
Flow : Break	1120	psi	
Tensile Elongation [2]			ISO 37
Across Flow : Break	700	%	
Flow : Break	750	%	
Tear Strength [3]			ISO 34-1
Across Flow	148	lbf/in	
Flow	160	lbf/in	
Compression Set [4]			ISO 815
73°F, 72 hr	34	%	
158°F, 22 hr	45	%	
212°F, 22 hr	60	%	
248°F, 22 hr	70	%	
Hardness	**Nominal Value**	**Unit**	**Test Method**
Shore Hardness (Shore A, Instant, Injection Molded)	79		ISO 868

+135-3858-6433 (GuangDong)
+188-1699-6168 (ShangHai)
+852-6957-5415 (HongKong)

Sarlink® TPE ML-1675B BLK

Teknor Apex Company - Thermoplastic Elastomer

Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air [5]			ISO 188
Across Flow : 248°F, 1000 hr	10	%	
Flow : 248°F, 1000 hr	-6.5	%	
Across Flow : 100% Strain 248°F, 1000 hr	13	%	
Flow : 100% Strain 248°F, 1000 hr	15	%	
Change in Tensile Strain at Break in Air [5]			ISO 188
Across Flow : 248°F, 1000 hr	-1.8	%	
Flow : 248°F, 1000 hr	-8.4	%	
Change in Shore Hardness in Air [6]			ISO 188
Shore A, 248°F, 1000 hr	-0.80		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 400	°F
Middle Temperature	380 to 440	°F
Front Temperature	400 to 460	°F
Nozzle Temperature	400 to 460	°F
Processing (Melt) Temp	400 to 460	°F
Mold Temperature	70 to 100	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] Type 2, 20 in/min

[3] Method Ba, Angle (Unnicked), 20 in/min

[4] Type A

[5] Type 2

[6] Instant