



TEKBOND® THERMOPLASTIC ELASTOMER

Typical Property Values - TEKBOND TB-6000-45					
PROPERTY*	TEST METHOD	TYPICAL VALUES	TEST UNITS	TYPICAL VALUES	TEST UNITS
HARDNESS	ASTM D-2240	45	Shore A		
SPECIFIC GRAVITY	ASTM D-792	1.00			
TENSILE STRENGTH	ASTM D-412	800	psi	5.5	MPa
ULTIMATE ELONGATION	ASTM D-412	500	%		
Compression Set 23°C	ASTM D-412	20	%		
MELT INDEX (G) 200°C/ 5 kg	ASTM D-1238	15	gms		
MOLD SHRINKAGE LENGTH WIDTH	ASTM D-955	0.0321 0.0214	in/in in/in		
FLAME CLASS	UL 94	HB			

*Not to be construed as specification.