



TEKBOND® THERMOPLASTIC ELASTOMER

Typical Property Values - TEKBOND 6000-60					
PROPERTY*	TEST METHOD	TYPICAL VALUES	TEST UNITS	TYPICAL VALUES	TEST UNITS
HARDNESS	ASTM D-2240	60	Shore A		
SPECIFIC GRAVITY	ASTM D-792	1.00			
TENSILE STRENGTH	ASTM D-412	1,200	psi	8.3	MPa
ULTIMATE ELONGATION	ASTM D-412	560	%		
MELT INDEX 200°C/ 5 kg	ASTM D-1238	10	gms		
MOLD SHRINKAGE		2.0	%		
FLAME CLASS	UL 94	HB			

*Not to be construed as specification.