



Telcar® GS7073A

Teknor Apex Asia Pacific PTE. LTD. - Thermoplastic Elastomer

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Uses	• Flexible Grips • Food Containers • Gaskets	• Overmolding • Pacifiers • Seats	• Toothbrush Handles • Tubing • Writing Instruments
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.02		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	15	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	435	psi	ASTM D412
Tensile Stress (300% Strain)	580	psi	ASTM D412
Tensile Strength (Break)	653	psi	ASTM D412
Tensile Elongation (Break)	380	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	70		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	104 to 176	°F
Rear Temperature	356 to 482	°F
Middle Temperature	356 to 482	°F
Front Temperature	356 to 482	°F
Mold Temperature	104 to 140	°F
Injection Pressure	1500 to 20000	psi
Injection Rate	Fast	

Injection Notes

Purging Material: HDPE, PP

Extrusion	Nominal Value	Unit
Drying Temperature	104 to 176	°F
Cylinder Zone 1 Temp.	338 to 446	°F
Cylinder Zone 2 Temp.	338 to 446	°F
Cylinder Zone 3 Temp.	338 to 446	°F
Cylinder Zone 4 Temp.	338 to 446	°F
Cylinder Zone 5 Temp.	338 to 446	°F

Extrusion Notes

Compression Ratio: 2.5 to 5.0

Purging Material: HDPE, PP

LD Ratio: 25:1 or higher

Notes

¹ Typical properties: these are not to be construed as specifications.