



Telcar® TL-2426D GRY 1093

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-2426D GRY 1093 is a thermoplastic elastomer designed for automotive and industrial applications. TL-2426D GRY 1093 is a medium hardness, low density grade that is RoHS compliant. This grade is suitable for both injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Low Density • Low Specific Gravity • Lubricated	• Medium Flow • Medium Hardness • Slip	• Without Fillers
Uses	• Automotive Applications • Caps	• Industrial Applications • Liners	
RoHS Compliance	• RoHS Compliant		
Appearance	• Grey		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.890		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	17	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	285	psi	
Flow : 100% Strain	314	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	373	psi	
Flow : 300% Strain	436	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	1320	psi	
Flow : Break	954	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	870	%	
Flow : Break	750	%	
Tear Strength ²			ASTM D624
Across Flow	172	lbf/in	
Flow	166	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	33	%	
158°F, 22 hr	58	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 1 sec, Injection Molded	68		
Shore A, 5 sec, Injection Molded	66		

Telcar® TL-2426D GRY 1093

Teknor Apex Company - Thermoplastic Elastomer

Processing Information		
Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	370 to 405	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 1