



Telcar® TL-2657J BLK

Teknor Apex Company - Thermoplastic Elastomer

General Information

Product Description

Telcar TL-2657J BLK is a general purpose thermoplastic elastomer designed for the industrial and transportation markets, including weatherstripping and wind skirts. Telcar TL-2657J BLK is a high hardness, high density, UV stable grade suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Filled • Good Color Stability • Good Melt Strength	• Good Mold Release • Good Moldability • Good Processability • High Density	• High Hardness • High Specific Gravity • Light Stabilized • Low Flow
Uses	• General Purpose • Grommets	• Industrial Applications • Rubber Replacement	• Weatherstripping
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	5.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	39300	psi	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	1110	psi	
Flow : 100% Strain	1400	psi	
Tensile Stress ²			ASTM D412
Across Flow : 300% Strain	1240	psi	
Flow : 300% Strain	1570	psi	
Tensile Strength ²			ASTM D412
Across Flow : Break	2480	psi	
Flow : Break	1930	psi	
Tensile Elongation ²			ASTM D412
Across Flow : Break	700	%	
Flow : Break	490	%	
Tear Strength ²			ASTM D624
Across Flow	327	lbf/in	
Flow	418	lbf/in	
Compression Set ³			ASTM D395B
73°F, 22 hr	31	%	
158°F, 22 hr	24	%	

Telcar® TL-2657J BLK

Teknor Apex Company - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A	95		
Shore D, 1 sec, Injection Molded ⁴	46		
Shore D, 5 sec, Injection Molded ⁴	45		

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	340 to 380	°F
Middle Temperature	350 to 390	°F
Front Temperature	360 to 400	°F
Nozzle Temperature	370 to 410	°F
Processing (Melt) Temp	370 to 410	°F
Mold Temperature	77 to 150	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Moderate-Fast	
Back Pressure	25.0 to 50.0	psi
Screw Speed	50 to 100	rpm
Cushion	0.150 to 1.00	in

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 370	°F
Cylinder Zone 2 Temp.	340 to 380	°F
Cylinder Zone 3 Temp.	350 to 390	°F
Cylinder Zone 4 Temp.	350 to 390	°F
Cylinder Zone 5 Temp.	360 to 400	°F
Die Temperature	374 to 410	°F

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C, 20 in/min

³ Type 2

⁴ Aged for 24 hr