



Sarlink® TPV 24960

Teknor Apex Company - Thermoplastic Vulcanizate

General Information

Product Description

Sarlink TPV 24960 is a high performance thermoplastic vulcanizate used in automotive and industrial applications. Sarlink TPV 24960 is a medium hardness, medium density, RoHS compliant grade exhibiting excellent UV resistance. This grade is suitable for injection molding and extrusion.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Chemical Resistant • Good Color Stability • Good Compression Set	• Good Processability • Low Fogging • Low Specific Gravity	• Medium Density • Medium Hardness • UV Resistant
Uses	• Expansion Joint • Gaskets • Glazing	• Grommets • Plugs • Shock Absorbing Pads	• Tubing • Weatherstripping
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.960		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength (Break)	580	psi	ASTM D412
Tensile Elongation (Break)	250	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	55		ASTM D2240

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	344 to 416	°F
Middle Temperature	354 to 426	°F
Front Temperature	364 to 436	°F
Nozzle Temperature	374 to 446	°F
Processing (Melt) Temp	374 to 446	°F
Mold Temperature	95 to 140	°F
Injection Pressure	200 to 1000	psi
Injection Rate	Fast	
Back Pressure	25.0 to 125	psi

Sarlink® TPV 24960

Teknor Apex Company - Thermoplastic Vulcanizate

Injection	Nominal Value	Unit
Screw Speed	50 to 120	rpm
Cushion	0.150 to 1.00	in
Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	330 to 400	°F
Cylinder Zone 2 Temp.	340 to 410	°F
Cylinder Zone 3 Temp.	350 to 420	°F
Cylinder Zone 5 Temp.	360 to 430	°F
Die Temperature	374 to 440	°F
Extrusion Notes		
Screw Speed: 30 to 100 rpm		

Notes

¹ Typical properties: these are not to be construed as specifications.