



Sarlink® TPV X11044DB

Teknor Apex Company - Thermoplastic Vulcanizate

General Information

Product Description

SARLINK® TPV 11000 series are engineered low friction slip coating materials designed primarily for demanding automotive and industrial applications. SARLINK® TPV X11044DB is a high hardness, low density grade with good UV resistance and superior abrasion resistance and can be co-extruded with TPE-S, TPE-V, and EPDM.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific • Europe	• Latin America • North America	
Features	• Bondability • Chemical Resistant • Good Adhesion • Good Processability	• High Hardness • High Heat Resistance • Low Compression Set • Low Density	• Low Friction • Low Specific Gravity • Specialty Grade • UV Resistant
Uses	• Automotive Applications • Automotive Exterior Parts • Automotive Window Encapsulation	• Coating Applications • Industrial Applications • Rubber Replacement	• Weatherstripping
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• DAIMLER DBL 5578 Color: Black • NISSAN Unspecified Color: Black	• VAG VW501 23 Color: Black • VAG VW501 2G Color: Black	
Appearance	• Black	• Opaque	
Forms	• Pellets		
Processing Method	• Coextrusion	• Extrusion	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	25100	psi	ASTM D790
Coefficient of Friction (vs. Glass - Dynamic)	0.25		ASTM D1894
Elastomers	Nominal Value	Unit	Test Method
Tensile Strength - Across Flow (Break)	1600	psi	ASTM D412
Tensile Elongation - Across Flow (Break)	550	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 5 sec, Injection Molded)	40		ASTM D2240
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (392°F, 206 sec ⁻¹)	312	Pa·s	ASTM D3835

Additional Information

Co-extrudes with good adhesion to TPE-S;
Co-extrudes with good adhesion to TPV;
Co-extrudes with good adhesion to EPDM

Sarlink® TPV X11044DB

Teknor Apex Company - Thermoplastic Vulcanizate

Processing Information		
Extrusion	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	350 to 410	°F
Cylinder Zone 2 Temp.	360 to 420	°F
Cylinder Zone 3 Temp.	380 to 440	°F
Cylinder Zone 4 Temp.	380 to 440	°F
Cylinder Zone 5 Temp.	380 to 440	°F
Die Temperature	380 to 440	°F

Notes

¹ Typical properties: these are not to be construed as specifications.