



Bergamid™ A65 GK15 natur SO

Polyamide 66

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Bead, 15% Filler by Weight
Features	• General Purpose • Good Flow
Forms	• Granules

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ² (73°F (23°C))	1.23 g/cm ³	1.23 g/cm ³	DIN 53479
Molding Shrinkage ³ 73°F (23°C), 0.157 in (4.00 mm)	1.4 to 1.9 %	1.4 to 1.9 %	ISO 294-4
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ⁴ 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	595000 psi	4100 MPa	ISO 527-2/1
Tensile Stress ⁴ Break, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	8700 psi	60.0 MPa	ISO 527-2/5
Tensile Strain ⁴ Break, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	1.5 %	1.5 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength -22°F (-30°C), Injection Molded	0.67 ft·lb/in ²	1.4 kJ/m ²	ISO 179
73°F (23°C) ⁴	1.2 ft·lb/in ²	2.5 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength -22°F (-30°C), Injection Molded	7.1 ft·lb/in ²	15 kJ/m ²	ISO 179
73°F (23°C), Injection Molded ⁴	7.1 ft·lb/in ²	15 kJ/m ²	ISO 179/1eA
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	434 °F	224 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	168 °F	75.5 °C	ISO 75-2/A
Maximum Use Temperature long term (GTP 50% tensile)	185 °F	85 °C	IEC 216
short time	356 °F	180 °C	IEC 60216
Melting Temperature (DSC)	502 °F	261 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity -- ⁴	1.0E+13 ohms	1.0E+13 ohms	IEC 93
-- ⁵	1.0E+10 ohms	1.0E+10 ohms	

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Volume Resistivity			IEC 93
-- ⁴	1.0E+15 ohms·cm	1.0E+15 ohms·cm	
-- ⁵	1.0E+12 ohms·cm	1.0E+12 ohms·cm	
Dissipation Factor ⁵ (1 MHz)	1.0E-4	1.0E-4	IEC 60250
Comparative Tracking Index ⁴ (Solution A)	500 V	500 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03

³ Bergmann method

⁴ dry

⁵ air humidity

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.