



Bergamid™ A700 G35 H (f1)

Polyamide 66

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe • Asia Pacific • North America
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Features	• Heat Stabilized
RoHS Compliance	• RoHS Compliant
UL File Number	• QMFZ2.E76261
Forms	• Pellets

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.41 g/cm ³	1.41 g/cm ³	DIN 53479
Dimensional Stability	0.0 %	0.0 %	ISO 2796
K-Value ³	74.0 to 78.0	74.0 to 78.0	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ⁴ (73°F (23°C))	1.67E+6 psi	11500 MPa	ISO 527-2
Tensile Stress (Break, 73°F (23°C))	29000 psi	200 MPa	ISO 527-2/5
Tensile Strain (Break, 73°F (23°C))	3.0 %	3.0 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/A
-22°F (-30°C)	5.7 ft·lb/in ²	12 kJ/m ²	
73°F (23°C)	6.7 ft·lb/in ²	14 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-22°F (-30°C)	36 ft·lb/in ²	75 kJ/m ²	
73°F (23°C)	43 ft·lb/in ²	90 kJ/m ²	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/B
66 psi (0.45 MPa), Unannealed	482 °F	250 °C	
Heat Deflection Temperature			ISO 75-2/A
264 psi (1.8 MPa), Unannealed	482 °F	250 °C	
Maximum Use Temperature			IEC 60216
-- ⁵	248 °F	120 °C	
Short Time	428 °F	220 °C	
Melting Temperature (DSC)	502 °F	261 °C	ISO 3146
RTI Elec			UL 746
0.028 in (0.70 mm)	212 °F	100 °C	
0.06 in (1.5 mm)	212 °F	100 °C	
0.12 in (3.0 mm)	212 °F	100 °C	
RTI Imp			UL 746
0.028 in (0.70 mm)	194 °F	90.0 °C	
0.06 in (1.5 mm)	194 °F	90.0 °C	
0.12 in (3.0 mm)	194 °F	90.0 °C	

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Thermal	Typical Value (English)	Typical Value (SI)	Test Method
RTI Str			UL 746
0.028 in (0.70 mm)	212 °F	100 °C	
0.06 in (1.5 mm)	221 °F	105 °C	
0.12 in (3.0 mm)	230 °F	110 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	> 1.0E+12 ohms	> 1.0E+12 ohms	IEC 60093
Volume Resistivity	> 1.0E+11 ohms·cm	> 1.0E+11 ohms·cm	IEC 60093
Dielectric Strength	530 V/mil	21 kV/mm	ASTM D149
Electric Strength	2300 V/mil	90 kV/mm	IEC 60243-1
Relative Permittivity (1 MHz)	3.70	3.70	IEC 60250
Arc Resistance	PLC 6	PLC 6	ASTM D495
Comparative Tracking Index (CTI)	PLC 0	PLC 0	UL 746
High Amp Arc Ignition (HAI)			UL 746
0.028 in (0.70 mm)	PLC 0	PLC 0	
0.06 in (1.5 mm)	PLC 0	PLC 0	
0.12 in (3.0 mm)	PLC 0	PLC 0	
High Voltage Arc Tracking Rate (HVTR)	PLC 0	PLC 0	UL 746
Hot-wire Ignition (HWI)			UL 746
0.028 in (0.70 mm)	PLC 4	PLC 4	
0.06 in (1.5 mm)	PLC 1	PLC 1	
0.12 in (3.0 mm)	PLC 0	PLC 0	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.028 in (0.70 mm), ALL	HB	HB	
0.06 in (1.5 mm), ALL	HB	HB	
0.12 in (3.0 mm), ALL	HB	HB	
Flammability Classification			IEC 60695-11-10, -20
0.12 in (3.0 mm), ALL	HB40	HB40	
0.028 in (0.70 mm), ALL	HB75	HB75	
0.06 in (1.5 mm), ALL	HB75	HB75	

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03 g/cm³

³ 96% H2SO4

⁴ 0.039 in/min (1 mm/min)

⁵ Continuous (GTP 50% Tensile)

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.