



OnFlex™ AF 7210-40

Thermoplastic Elastomer

Key Characteristics

Product Description

OnFlex™ AF 7210-40 is an easy processing TPE designed for a variety of automotive applications.

- Excellent surface finish
- Good adhesion to polypropylene
- Excellent performance in static mechanical parts such as seals & grips, panel fasteners, plugs, clips and cable clamps.
- Good UV stability
- OnFlex™ AF 7210-40B = black
- OnFlex™ AF 7210-40N = natural

General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Europe	• North America
Features	• Good Processability		
Uses	• Automotive Applications • Fasteners	• Gaskets • Overmolding	• Plugs
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density			
-- ²	0.990 g/cm ³	0.990 g/cm ³	ISO 1183
-- ³	0.990 g/cm ³	0.990 g/cm ³	ASTM D792
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength			
Break ²	725 psi	5.00 MPa	ISO 37
Break ³	725 psi	5.00 MPa	ASTM D412
Tensile Elongation			
Break ²	600 %	600 %	ISO 37
Break ³	650 %	650 %	ASTM D412
Tear Strength			
-- ²	120 lbf/in	21.0 kN/m	ISO 34-1
-- ³	100 lbf/in	17.5 kN/m	ASTM D624
Compression Set			
73°F (23°C), 72 hr ²	16 %	16 %	ISO 815
73°F (23°C), 72 hr ³	18 %	18 %	ASTM D395
158°F (70°C), 22 hr ²	32 %	32 %	ISO 815
158°F (70°C), 22 hr ³	35 %	35 %	ASTM D395
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness			
Shore A, 3 sec ²	40	40	ISO 868
Shore A, 10 sec ³	36	36	ASTM D2240

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Burning Rate	< 3.9 in/min	< 100 mm/min	DIN 75200
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Weather Resistance ⁴	expected to pass	expected to pass	SAE J2527

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	320 to 370 °F	160 to 188 °C
Middle Temperature	350 to 380 °F	177 to 193 °C
Front Temperature	370 to 410 °F	188 to 210 °C
Nozzle Temperature	370 to 420 °F	188 to 216 °C
Mold Temperature	86.0 to 140 °F	30.0 to 60.0 °C
Injection Rate	Fast	Fast
Back Pressure	0.00 to 120 psi	0.00 to 0.827 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

Notes

¹ Typical values are not to be construed as specifications.

² Europe

³ China

⁴ OnFlex AF 7210-60B (60Sh; black) as part of the AF-range has been tested according weathering test SAE J2527. It has successfully passed the extended test time of 1500h.

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.