



# LubriOne™ ATH-000/04S NATURAL

## Acetal (POM) Homopolymer

### Key Characteristics

Product Description			
LubriOne™ Lubricated and Wear-Resistant Compounds have been specifically formulated to be self-lubricating materials, offering low coefficient of friction and improved wear resistance properties. LubriOne compounds have been demonstrated to reduce friction, noise, vibration, heat buildup and improve product durability.			
General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Homopolymer	• Low Friction	• Lubricated
Uses	• Appliance Components • Automotive Applications • Bearings • Business Equipment	• Consumer Applications • Conveyor Parts • Gears • Industrial Applications	• Printer Parts • Pulleys • Rollers
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.38	1.38	ASTM D792
Molding Shrinkage - Flow	0.020 to 0.040 in/in	2.0 to 4.0 %	ASTM D955
Molding Shrinkage - Across Flow	0.010 to 0.030 in/in	1.0 to 3.0 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus <sup>2</sup>	280000 psi	1930 MPa	ASTM D638
Tensile Strength <sup>2</sup> (Yield)	7300 psi	50.3 MPa	ASTM D638
Tensile Strength <sup>2</sup> (Break)	7300 psi	50.3 MPa	ASTM D638
Flexural Modulus <sup>3</sup>	329000 psi	2270 MPa	ASTM D790
Flexural Strength <sup>3</sup>	11000 psi	75.8 MPa	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.11	0.11	
vs. Steel - Static	0.15	0.15	
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256A
73°F (23°C), 0.250 in (6.35 mm), Injection Molded	1.1 ft-lb/in	60 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	316 °F	158 °C	
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed	188 °F	86.7 °C	

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

## Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	200 °F	93.3 °C
Drying Time	1.0 to 2.0 hr	1.0 to 2.0 hr
Suggested Max Moisture	0.15 to 0.20 %	0.15 to 0.20 %
Rear Temperature	330 to 350 °F	166 to 177 °C
Middle Temperature	350 to 370 °F	177 to 188 °C
Front Temperature	370 to 390 °F	188 to 199 °C
Nozzle Temperature	380 to 410 °F	193 to 210 °C
Mold Temperature	170 to 200 °F	76.7 to 93.3 °C

## Notes

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> Type I, 0.20 in/min (5.1 mm/min)

<sup>3</sup> 0.050 in/min (1.3 mm/min)

## CONTACT INFORMATION

## Americas

United States - Avon Lake  
+1 440 930 1000

United States - McHenry  
+1 815 385 8500

## Asia

China - Guangzhou  
+86 20 8732 7260

China - Shenzhen  
+86 755 2969 2888

China - Suzhou  
+86 512 6823 24 38

China - Suzhou  
+86 512 6265 2600

Hong Kong -  
+852 2690 5332

Taiwan - Yonghe City,  
+886 9396 99740, +886 2929 1849

## Europe

Germany - Gaggenau  
+49 7225 6802 0

Spain - Barbastro (Huesca)  
+34 974 310 314



*Beyond Polymers.*

*Better Business Solutions. SM*

www.polyone.com

## PolyOne Americas

33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE

## PolyOne Asia

No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 201203, China  
+86 21 5080 1188

## PolyOne Europe

6 Gälllewee  
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.