



Bergamid™ B70 VN4805 LS PM-Z BK

Polyamide 6

Key Characteristics

Product Description	
6013041	
General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Features	• Impact Modified • Laser Markable
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density ² (73°F (23°C))	1.07	1.07	g/cm ³	ISO 1183
Molding Shrinkage - Flow ³				ISO 294-4
73°F (23°C), 0.157 in (4.00 mm)	2.0	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				ISO 527-2/50
73°F (23°C), 0.157 in (4.00 mm), Injection Molded	290000 (2000)	152000 (1050)	psi (MPa)	
Tensile Stress				ISO 527-2/50
Yield, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	6240 (43.0)	4060 (28.0)	psi (MPa)	
Tensile Strain				ISO 527-2/50
Yield, 73°F (23°C), 0.157 in (4.00 mm)	3.0	4.0	%	
Tensile Strain				ISO 527-2/50
Break, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	> 80	> 150	%	
Flexural Modulus				ISO 178
73°F (23°C), Injection Molded	174000 (1200)	65300 (450)	psi (MPa)	
Flexural Stress				ISO 178
73°F (23°C), Injection Molded	6090 (42.0)	1890 (13.0)	psi (MPa)	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
73°F (23°C), Injection Molded	42 (89)	44 (93)	ft-lb/in ² (kJ/m ²)	
Charpy Unnotched Impact Strength				ISO 179
-22°F (-30°C), Injection Molded	No Break	No Break		
73°F (23°C), Injection Molded	No Break	No Break		

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Thermal	Dry	Conditioned	Unit	Test Method
Vicat Softening Temperature	329 (165)	--	°F (°C)	ISO 306/B
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+15	1.0E+15	ohms	ASTM D257
Volume Resistivity	1.0E+15	1.0E+15	ohms·cm	ASTM D257
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.13 in (3.2 mm), ALL)	HB	HB		UL 94

Processing Information

Injection	Dry (English)	Dry (SI)
Drying Temperature	140 °F	60.0 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	464 to 500 °F	240 to 260 °C
Mold Temperature	140 to 176 °F	60.0 to 80.0 °C

Notes

¹ Typical values are not to be construed as specifications.

² ±0.02

³ Bergmann method

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giallewee
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.