



# Bergaflex™ BFI 65A-312

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

Bergaflex™ BFI 65A-312 is an easy processing, general purpose thermoplastic elastomer based on styrenic block copolymers. Material is filled and is therefore opaque and has a high density.

#### General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Europe	• North America
Features	• General Purpose	• Good Flow	• Good Processability
Uses	• Appliances • Automotive Applications	• Consumer Applications • General Purpose	• Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.17	1.17	ISO 1183
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress <sup>2</sup>			ISO 37
Break, 73°F (23°C), 0.0787 in (2.00 mm)	943 psi	6.50 MPa	
Tensile Elongation <sup>2</sup>			ISO 37
Break, 73°F (23°C), 0.0787 in (2.00 mm)	650 %	650 %	
Compression Set			ISO 815
73°F (23°C), 72 hr	19 %	19 %	
158°F (70°C), 22 hr	42 %	42 %	
212°F (100°C), 22 hr	80 %	80 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness <sup>3</sup>			ISO 7619
Shore A, 10 sec, 73°F (23°C), Injection Molded	65	65	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	329 to 347 °F	165 to 175 °C
Middle Temperature	347 to 383 °F	175 to 195 °C
Front Temperature	365 to 437 °F	185 to 225 °C
Nozzle Temperature	383 to 437 °F	195 to 225 °C
Mold Temperature	68 to 104 °F	20 to 40 °C
Back Pressure	290 to 1450 psi	2.00 to 10.0 MPa
Screw Speed	40 to 100 rpm	40 to 100 rpm

**Injection Notes**

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Regrind levels up to 20% can be used with Bergaflex™ BFI 65A-312 with minimal property losses, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should be as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Bergaflex BFI 65A-312 has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8-10 minutes or longer.

Drying is not Required

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 7.9 in/min (200 mm/min)

<sup>3</sup> ±5 Sh A



*Beyond Polymers.*

*Better Business Solutions.™*