



# Bergamid™ A65 G25 U Black 70

## Polyamide 66

### Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Features	• Flame Retardant • Good Hardness • Good Impact Resistance	• Good Processability • Good Stiffness • Good Strength	• Medium Viscosity
Uses	• Appliances • Automotive Applications	• Consumer Applications • Electrical/Electronic Applications	• General Purpose • Industrial Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.55 g/cm <sup>3</sup>	1.55 g/cm <sup>3</sup>	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.31E+6 psi	9000 MPa	ISO 527-2/1
Tensile Stress	18900 psi	130 MPa	ISO 527-2/5
Tensile Strain (Break)	2.5 %	2.5 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	4.0 ft·lb/in <sup>2</sup>	8.5 kJ/m <sup>2</sup>	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	500 to 509 °F	260 to 265 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	UL 94
Glow Wire Flammability Index 0.04 to 0.12 in (1.0 to 3.0 mm)	1760 °F	960 °C	IEC 60695-2-12
Glow Wire Ignition Temperature 0.06 to 0.08 in (1.5 to 2.0 mm)	1560 °F	850 °C	IEC 60695-2-13
0.04 to 0.12 in (1.0 to 3.0 mm)	1520 °F	825 °C	
0.12 in (3.0 mm)	1610 °F	875 °C	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	527 to 545 °F	275 to 285 °C
Middle Temperature	536 to 554 °F	280 to 290 °C
Front Temperature	545 to 563 °F	285 to 295 °C
Nozzle Temperature	563 to 572 °F	295 to 300 °C
Mold Temperature	176 °F	80 °C