



Bergamid™ A65 TF12 natural Polyamide 66

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Features	• Lubricated
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.21 g/cm ³	1.21 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	421000 psi	2900 MPa	ISO 527-2
Tensile Stress (Break)	10900 psi	75.0 MPa	ISO 527-2
Tensile Strain (Break)	> 10 %	> 10 %	ISO 527-2
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	2.4 ft·lb/in ²	5.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	31 ft·lb/in ²	65 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	428 °F	220 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	176 °F	80.0 °C	ISO 75-2/A
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+13 ohms	1.0E+13 ohms	IEC 60093
Volume Resistivity	1.0E+15 ohms·cm	1.0E+15 ohms·cm	IEC 60093
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating 0.03 to 0.06 in (0.8 to 1.6 mm)	HB	HB	UL 94

Notes

¹ Typical values are not to be construed as specifications.