

Bergamid™ A70 C10 black

Polyamide 66

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe
Filler / Reinforcement	• Carbon Fiber, 10% Filler by Weight
Features	• Electrically Conductive
Appearance	• Black
Forms	• Pellets

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.18 g/cm ³	1.18 g/cm ³	ISO 1183
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.9 ft·lb/in ²	4.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	14 ft·lb/in ²	30 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Melting Temperature (DSC)	491 to 509 °F	255 to 265 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+2 to 1.0E+4 ohms	1.0E+2 to 1.0E+4 ohms	IEC 60093

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	536 to 572 °F	280 to 300 °C
Mold Temperature	122 to 194 °F	50 to 90 °C

Notes

¹ Typical values are not to be construed as specifications.

² ±0.02