



# Bergamid™ A70 G10 H BK032

## Polyamide 66

### Key Characteristics

Product Description	
Heat stabilized, glass fiber reinforced PA66 compounds	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized
Appearance	• Black
Processing Method	• Injection Molding

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.21	1.21	ASTM D792
Molding Shrinkage - Flow	7.0E-3 to 0.014 in/in	0.70 to 1.4 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength <sup>2</sup>	16000 psi	110 MPa	ASTM D638
Flexural Modulus <sup>3</sup>	653000 psi	4500 MPa	ASTM D790
Flexural Strength <sup>3</sup>	23200 psi	160 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm)	0.75 ft-lb/in	40 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	410 °F	210 °C	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	500 to 536 °F	260 to 280 °C
Middle Temperature	500 to 536 °F	260 to 280 °C
Front Temperature	500 to 536 °F	260 to 280 °C
Mold Temperature	149 to 185 °F	65 to 85 °C

Injection Notes
Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

---

<sup>2</sup> 0.20 in/min (5.0 mm/min)

---

<sup>3</sup> 0.051 in/min (1.3 mm/min)