



Bergamid™ A70 G25 Black

Polyamide 66

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Uses	• Appliances • Consumer Applications • Industrial Applications • Automotive Applications • General Purpose
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.32 g/cm ³	1.32 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.19E+6 psi	8200 MPa	ISO 527-2/1
Tensile Stress	23200 psi	160 MPa	ISO 527-2/5
Tensile Strain (Break)	3.0 %	3.0 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength	4.8 ft-lb/in ²	10 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	31 ft-lb/in ²	65 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Melting Temperature (DSC)	502 °F	261 °C	ISO 3146

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Rear Temperature	527 to 545 °F	275 to 285 °C
Middle Temperature	536 to 554 °F	280 to 290 °C
Front Temperature	545 to 563 °F	285 to 295 °C
Nozzle Temperature	563 to 572 °F	295 to 300 °C
Mold Temperature	176 °F	80 °C

Notes

¹ Typical values are not to be construed as specifications.