

Bergamid™ A70 G25 H U BLACK SO V2

Polyamide 66

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Additive	• Heat Stabilizer
Features	• Flame Retardant • Heat Stabilized • Halogen Free • High Impact Resistance
RoHS Compliance	• RoHS Compliant
Forms	• Pellets

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ² (73°F (23°C))	1.38 g/cm ³	1.38 g/cm ³	DIN 53479
Ash Content	> 25 %	> 25 %	ISO 3451
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	1.38E+6 psi	9500 MPa	ISO 527-2/1
Tensile Stress Break, 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	22900 psi	158 MPa	ISO 527-2/5
Tensile Strain (Break, 73°F (23°C))	2.7 %	2.7 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	3.6 ft·lb/in ²	7.5 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength -22°F (-30°C)	31 ft·lb/in ²	66 kJ/m ²	ISO 179/1eA
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	482 °F	250 °C	ISO 75-2/B
Maximum Use Temperature -- ³ Short Time	248 °F 428 °F	120 °C 220 °C	IEC 60216
Melting Temperature (DSC)	502 °F	261 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+13 ohms	1.0E+13 ohms	IEC 60093
Volume Resistivity	1.0E+15 ohms·cm	1.0E+15 ohms·cm	IEC 60093
Comparative Tracking Index (Solution A)	> 400 V	> 400 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			UL 94
0.031 in (0.8 mm)	V-2	V-2	
0.06 in (1.6 mm)	V-1	V-1	
0.12 in (3.0 mm)	V-0	V-0	

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Glow Wire Flammability Index 0.03 to 0.12 in (0.8 to 3.0 mm)	1760 °F	960 °C	IEC 60695-2-12

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03 g/cm³

³ Continuous (GTP 50% Tensile)