



Bergamid™ A70 G25 H U Natural 70

Polyamide 66

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Features	• Flame Retardant • Good Heat Resistance • Good Impact Resistance	• Good Processability • Good Stiffness • Good Strength	• Heat Stabilized • Medium Viscosity
Uses	• Appliances • Automotive Applications	• Consumer Applications • General Purpose	• Industrial Applications
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.55 g/cm ³	1.55 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.38E+6 psi	9500 MPa	ISO 527-2/1
Tensile Stress	19600 psi	135 MPa	ISO 527-2/5
Tensile Strain (Break)	2.2 %	2.2 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	4.0 ft·lb/in ²	8.5 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	500 to 509 °F	260 to 265 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-0	V-0	UL 94
Glow Wire Flammability Index 0.08 in (2.0 mm)	1760 °F	960 °C	IEC 60695-2-12

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Rear Temperature	527 to 545 °F	275 to 285 °C
Middle Temperature	536 to 554 °F	280 to 290 °C
Front Temperature	545 to 563 °F	285 to 295 °C
Nozzle Temperature	563 to 572 °F	295 to 300 °C
Mold Temperature	176 °F	80 °C

Notes

¹ Typical values are not to be construed as specifications.