



Bergamid™ A70 G30 Black TM-X 70 X1

Polyamide 66

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Good Hardness • Good Processability • Good Stiffness	• Good Strength • High Impact Resistance • Impact Modified	• Medium Viscosity
Uses	• Appliances • Automotive Applications	• Consumer Applications • General Purpose	• Industrial Applications
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.29 g/cm ³	1.29 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	943000 psi	6500 MPa	ISO 527-2/1
Tensile Stress	15200 psi	105 MPa	ISO 527-2/5
Tensile Strain (Break)	3.7 %	3.7 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact Strength	8.1 ft·lb/in ²	17 kJ/m ²	ISO 180/A
Thermal	Typical Value (English)	Typical Value (SI)	
Melting Temperature	500 to 509 °F	260 to 265 °C	
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	527 to 545 °F	275 to 285 °C
Middle Temperature	536 to 554 °F	280 to 290 °C
Front Temperature	545 to 563 °F	285 to 295 °C
Nozzle Temperature	554 to 572 °F	290 to 300 °C
Mold Temperature	176 °F	80 °C

Notes

¹ Typical values are not to be construed as specifications.