



Bergamid™ B70 G15 H TM-Z SO6

Polyamide 6

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • North America	
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight		
Features	• Good Color Stability	• High Heat Resistance	• High Impact Resistance
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ² (73°F (23°C))	1.17 g/cm ³	1.17 g/cm ³	DIN 53479
Melt Mass-Flow Rate (MFR) (235°C/2.16 kg)	> 6.0 g/10 min	> 6.0 g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (235°C/2.16 kg)	> 5.00 cm ³ /10min	> 5.00 cm ³ /10min	ISO 1133
Ash Content	15 %	15 %	ISO 3451
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus 73°F (23°C), 0.157 in (4.00 mm)	783000 psi	5400 MPa	ISO 527-2/1
Tensile Stress Break, 73°F (23°C), 0.157 in (4.00 mm)	14500 psi	100 MPa	ISO 527-2/5
Tensile Strain Break, 73°F (23°C), 0.157 in (4.00 mm)	> 4.0 %	> 4.0 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	> 8.1 ft·lb/in ²	> 17 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	36 ft·lb/in ²	75 kJ/m ²	ISO 179/1eU
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	401 °F	205 °C	ISO 75-2/B
Maximum Use Temperature -- ³	203 °F	95 °C	IEC 60216
Short Time	374 °F	190 °C	
Melting Temperature (DSC)	433 °F	223 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+12 ohms	1.0E+12 ohms	IEC 60093
Volume Resistivity	1.0E+13 ohms·cm	1.0E+13 ohms·cm	IEC 60093

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03 g/cm³

³ Continuous (GTP 50% Tensile)