



Bergamid™ B70 G30 H white VN8080CF UV

Polyamide 6

Key Characteristics

General			
Material Status	• Commercial: Active		
Regional Availability	• Europe		
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Good Dimensional Stability • Good Stiffness • Good Flow • Halogen Free • UV Resistant		
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity ²	1.35	1.35	DIN 53479
Molding Shrinkage - Flow ³ 73°F (23°C), 0.157 in (4.00 mm)	0.20 to 0.70 %	0.20 to 0.70 %	ISO 294-4
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus 73°F (23°C), 0.157 in (4.00 mm), Injection Molded	1.48E+6 psi	10200 MPa	ISO 527-2/1
Tensile Strength ⁴ 73°F (23°C), 0.157 in (4.00 mm)	23200 psi	160 MPa	ISO 527
Tensile Elongation ⁴ Break, 73°F (23°C), 0.157 in (4.00 mm)	2.6 %	2.6 %	ISO 527
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength	5.5 ft·lb/in ²	12 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	35 ft·lb/in ²	73 kJ/m ²	ISO 179
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+13 ohms	1.0E+13 ohms	IEC 60093
Volume Resistivity	1.0E+15 ohms·cm	1.0E+15 ohms·cm	IEC 60093
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating 0.03 to 0.12 in (0.8 to 3.0 mm), ALL	HB	HB	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 hr	4.0 hr
Processing (Melt) Temp	464 to 536 °F	240 to 280 °C
Mold Temperature	149 to 185 °F	65 to 85 °C

Notes

¹ Typical values are not to be construed as specifications.

² ± 0.03

³ Bergmann method

⁴ 0.20 in/min (5.0 mm/min)
