



Bergamid™ B70 G30 NC213

Polyamide 6

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Natural Color
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.36	1.36	ASTM D792
Molding Shrinkage - Flow	3.0E-3 to 6.0E-3 in/in	0.30 to 0.60 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	23900 psi	165 MPa	ASTM D638
Flexural Modulus ³	1.23E+6 psi	8500 MPa	ASTM D790
Flexural Strength ³	36300 psi	250 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm)	2.4 ft·lb/in	130 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	410 °F	210 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	464 to 536 °F	240 to 280 °C
Middle Temperature	464 to 536 °F	240 to 280 °C
Front Temperature	464 to 536 °F	240 to 280 °C
Mold Temperature	149 to 185 °F	65 to 85 °C

Injection Notes

Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.0 mm/min)

³ 0.051 in/min (1.3 mm/min)