



Bergamid™ B70 G30 Natural FD

Polyamide 6

Key Characteristics

General		
Material Status	• Commercial: Active	
Regional Availability	• Africa & Middle East	• Europe
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight	
Appearance	• Natural Color	
Forms	• Pellets	
Processing Method	• Injection Molding	

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.34 to 1.38	1.34 to 1.38	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	1.38E+6 psi	9500 MPa	ISO 527-2
Tensile Stress	26100 psi	180 MPa	ISO 527-2
Tensile Strain (Break)	< 3.5 %	< 3.5 %	ISO 527-2
Flexural Stress	36300 psi	250 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	7.1 ft·lb/in ²	15 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	43 ft·lb/in ²	90 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	> 428 °F	> 220 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Annealed	> 410 °F	> 210 °C	ISO 75-2/A
Melting Temperature (DSC)	419 to 437 °F	215 to 225 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Comparative Tracking Index (Solution A)	450 V	450 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm))	HB	HB	Internal Method
FMVSS Flammability	< 3.9 in/min	< 100 mm/min	DIN 75200

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C
Mold Temperature	122 to 194 °F	50 to 90 °C

Notes

¹ Typical values are not to be construed as specifications.