



Bergamid™ B70 G40 H BK039

Polyamide 6

Key Characteristics

Product Description	
Heat resistant	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• Medium Heat Resistance
Appearance	• Black
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density	1.47 g/cm ³	1.47 g/cm ³	ISO 1183
Molding Shrinkage	0.30 to 0.50 %	0.30 to 0.50 %	ISO 294-4
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress	26800 psi	185 MPa	ISO 527-2
Flexural Modulus	1.60E+6 psi	11000 MPa	ISO 178
Flexural Stress	40600 psi	280 MPa	ISO 178
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength	6.2 ft-lb/in ²	13 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	419 °F	215 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	464 to 536 °F	240 to 280 °C
Middle Temperature	464 to 536 °F	240 to 280 °C
Front Temperature	464 to 536 °F	240 to 280 °C
Mold Temperature	149 to 185 °F	65 to 85 °C

Injection Notes	
Injection Pressure: MED-HIGH	
Hold Pressure: MED-HIGH	
Screw Speed: MODERATE	
Back Pressure: LOW	

Notes

¹ Typical values are not to be construed as specifications.