



Bergamid™ B70 G60 H BK037

Polyamide 6

Key Characteristics

Product Description	
Glass Fiber Reinforced PA6 Compound with Heat Stabilized.	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Filler / Reinforcement	• Glass Fiber, 60% Filler by Weight
Features	• Medium Heat Resistance
Appearance	• Black
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.72	1.72	ASTM D792
Molding Shrinkage	0.10 to 0.50 %	0.10 to 0.50 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	26100 psi	180 MPa	ASTM D638
Flexural Modulus ³	2.47E+6 psi	17000 MPa	ASTM D790
Flexural Strength ³	46400 psi	320 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm)	2.8 ft-lb/in	150 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	419 °F	215 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	> 1.0E+12 ohms	> 1.0E+12 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	464 to 536 °F	240 to 280 °C
Middle Temperature	464 to 536 °F	240 to 280 °C
Front Temperature	464 to 536 °F	240 to 280 °C
Mold Temperature	158 to 194 °F	70 to 90 °C

Injection Notes	
Injection Pressure: MED-HIGH	
Hold Pressure: MED-HIGH	
Screw Speed: MODERATE	
Back Pressure: LOW	

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.0 mm/min)

³ 0.051 in/min (1.3 mm/min)