



Bergamid™ B70 GK30 UV

Polyamide 6

Key Characteristics

Product Description	
PA6 + Glass Bead	
General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Bead, 30% Filler by Weight
Features	• UV Stabilized
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity ²	1.35	1.35	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	609000 psi	4200 MPa	ISO 527-2
Tensile Strength (73°F (23°C))	8700 psi	60.0 MPa	ISO 527
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.4 ft·lb/in ²	3.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	356 °F	180 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	194 °F	90.0 °C	ISO 75-2/A
Continuous Use Temperature	212 °F	100 °C	IEC 216
Melting Temperature	433 °F	223 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+13 ohms	1.0E+13 ohms	ASTM D257
Volume Resistivity	1.0E+15 ohms·cm	1.0E+15 ohms·cm	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating			Internal Method
0.031 in (0.8 mm)	HB	HB	
0.06 in (1.6 mm)	HB	HB	

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	4.0 hr	4.0 hr
Suggested Max Moisture	0.10 %	0.10 %
Processing (Melt) Temp	464 to 536 °F	240 to 280 °C

Injection	Typical Value (English)	Typical Value (SI)
Mold Temperature	140 to 194 °F	60 to 90 °C

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03