



Bergamid™ B70 G/GK30 brown VN7751CF UV Polyamide 6

Key Characteristics

Product Description

Bergamid B70 G/GK30 is a Polyamide 6 (Nylon 6) product filled with 30% glass fiber + glass beads. It can be processed by injection molding.

General

Material Status	• Commercial: Active
Regional Availability	• Europe
Filler / Reinforcement	• Glass Bead\Glass Fiber, 30% Filler by Weight
Features	• Good Processability
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.36 g/cm ³	1.36 g/cm ³	ISO 1183
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	885000 psi	6100 MPa	ISO 527-2
Tensile Stress	16000 psi	110 MPa	ISO 527-2
Tensile Strain (Break)	2.0 to 5.0 %	2.0 to 5.0 %	ISO 527
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength (73°F (23°C))	1.9 ft·lb/in ²	4.0 kJ/m ²	ISO 179
Charpy Unnotched Impact Strength 73°F (23°C)	17 ft·lb/in ²	35 kJ/m ²	ISO 179
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	410 °F	210 °C	ISO 75-2/B
Heat Deflection Temperature 264 psi (1.8 MPa), Unannealed	374 °F	190 °C	ISO 75-2/A
Melting Temperature (DSC)	419 to 437 °F	215 to 225 °C	ISO 3146
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.13 in (3.2 mm))	HB	HB	UL 94

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Processing (Melt) Temp	500 to 554 °F	260 to 290 °C
Mold Temperature	122 to 194 °F	50 to 90 °C

Notes

¹ Typical values are not to be construed as specifications.

² ±0.02