



Bergamid™ B70 NC704

Polyamide 6

Key Characteristics

Product Description	
PA6 compound	
General	
Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Appearance	• Natural Color
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.13	1.13	ASTM D792
Molding Shrinkage	1.2 to 1.6 %	1.2 to 1.6 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	10900 psi	75.0 MPa	ASTM D638
Flexural Modulus ³	377000 psi	2600 MPa	ASTM D790
Flexural Strength ³	14500 psi	100 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.126 in (3.20 mm)	0.56 ft-lb/in	30 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	149 °F	65.0 °C	ASTM D648
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	> 1.0E+12 ohms	> 1.0E+12 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	V-2	V-2	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	464 to 536 °F	240 to 280 °C
Mold Temperature	149 to 185 °F	65 to 85 °C
Injection Notes		
Injection Pressure: MED-HIGH		
Hold Pressure: MED-HIGH		
Screw Speed: MODERATE		
Back Pressure: LOW		

Notes

¹ Typical values are not to be construed as specifications.

² 2.0 in/min (50 mm/min)

³ 0.051 in/min (1.3 mm/min)