



Bergamid™ B70 W25 natural FD

Polyamide 6

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Europe
Features	• Impact Modified
RoHS Compliance	• RoHS Compliant
Forms	• Pellets

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.12 g/cm ³	1.12 g/cm ³	DIN 53479
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus	334000 psi	2300 MPa	ISO 527-2
Tensile Stress (Break)	10900 psi	75.0 MPa	ISO 527-2
Tensile Strain (Break)	> 30 %	> 30 %	ISO 527-2
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F (-30°C)	2.4 ft·lb/in ²	5.0 kJ/m ²	
73°F (23°C)	3.3 ft·lb/in ²	7.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-22°F (-30°C)	No Break	No Break	
73°F (23°C)	No Break	No Break	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+13 ohms	1.0E+13 ohms	IEC 60093
Volume Resistivity	1.0E+15 ohms·cm	1.0E+15 ohms·cm	IEC 60093
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Burning Rate (0.0630 in (1.60 mm))	< 3.9 in/min	< 100 mm/min	FMVSS
Flame Rating			UL 94
0.031 in (0.8 mm)	HB	HB	
0.06 in (1.6 mm)	HB	HB	

Notes

¹ Typical values are not to be construed as specifications.

² ±0.02 g/cm³