



Bergamid™ B700 G15 H

Polyamide 6

Key Characteristics

General	
Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe • Asia Pacific • North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Features	• Heat Stabilized
RoHS Compliance	• RoHS Compliant
UL File Number	• QMFZ2.E76261
Forms	• Pellets

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density ²	1.23 g/cm ³	1.23 g/cm ³	DIN 53479
K-Value ³	74.0 to 78.0	74.0 to 78.0	
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	870000 psi	6000 MPa	ISO 527-2/1
Tensile Stress (Break, 73°F (23°C))	18900 psi	130 MPa	ISO 527-2/5
Tensile Strain (Break, 73°F (23°C))	3.5 %	3.5 %	ISO 527-2/5
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/A
-22°F (-30°C)	2.4 ft·lb/in ²	5.0 kJ/m ²	
73°F (23°C)	2.9 ft·lb/in ²	6.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-22°F (-30°C)	17 ft·lb/in ²	35 kJ/m ²	
73°F (23°C)	21 ft·lb/in ²	45 kJ/m ²	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Heat Deflection Temperature			ISO 75-2/B
66 psi (0.45 MPa), Unannealed	428 °F	220 °C	
Heat Deflection Temperature			ISO 75-2/A
264 psi (1.8 MPa), Unannealed	401 °F	205 °C	
Maximum Use Temperature			IEC 60216
-- ⁴	248 °F	120 °C	
Short Time	374 °F	190 °C	
Melting Temperature (DSC)	433 °F	223 °C	ISO 3146
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	> 1.0E+12 ohms	> 1.0E+12 ohms	IEC 60093
Volume Resistivity	> 1.0E+14 ohms·cm	> 1.0E+14 ohms·cm	IEC 60093
Relative Permittivity (1 MHz)	3.70	3.70	IEC 60250
Comparative Tracking Index (Solution A)	500 V	500 V	IEC 60112
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Burning Rate (0.0630 in (1.60 mm))	< 3.9 in/min	< 100 mm/min	FMVSS
Flame Rating			UL 94
0.03 to 0.12 in (0.8 to 3.0 mm), ALL	HB	HB	

Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Glow Wire Flammability Index 0.02 to 0.12 in (0.4 to 3.0 mm)	1200 °F	650 °C	IEC 60695-2-12
Glow Wire Ignition Temperature 0.02 to 0.12 in (0.4 to 3.0 mm)	1250 °F	675 °C	IEC 60695-2-13

Notes

¹ Typical values are not to be construed as specifications.

² ±0.03 g/cm³

³ 96% H₂SO₄

⁴ Continuous (GTP 50% Tensile)