



Bergamid™ BG6000-8031 HI BK001

Polyamide 6

Key Characteristics

Product Description

PA6 Compound with Impact Modified.

General

Material Status	• Commercial: Active
Regional Availability	• Asia Pacific
Additive	• Impact Modifier
Features	• Impact Modified
Appearance	• Black
Processing Method	• Injection Molding

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10	ASTM D792
Molding Shrinkage	1.2 to 1.6 %	1.2 to 1.6 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Strength ²	8700 psi	60.0 MPa	ASTM D638
Flexural Modulus ³	297000 psi	2050 MPa	ASTM D790
Flexural Strength ³	10200 psi	70.0 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.126 in (3.20 mm)	5.6 ft-lb/in	300 J/m	
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi (1.8 MPa), Unannealed, 0.126 in (3.20 mm)	149 °F	65.0 °C	
Electrical	Typical Value (English)	Typical Value (SI)	Test Method
Surface Resistivity	1.0E+15 ohms	1.0E+15 ohms	ASTM D257
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Flame Rating (0.06 in (1.6 mm))	HB	HB	Internal Method

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	176 to 194 °F	80 to 90 °C
Drying Time	4.0 to 6.0 hr	4.0 to 6.0 hr
Rear Temperature	464 to 536 °F	240 to 280 °C
Middle Temperature	464 to 536 °F	240 to 280 °C
Front Temperature	464 to 536 °F	240 to 280 °C
Mold Temperature	149 to 185 °F	65 to 85 °C

Injection Notes

Injection Pressure: MED-HIGH
Hold Pressure: MED-HIGH
Screw Speed: MODERATE
Back Pressure: LOW

Notes

¹ Typical values are not to be construed as specifications.

² 2.0 in/min (50 mm/min)

³ 0.051 in/min (1.3 mm/min)