



# Versaflex™ CE 3180

## Thermoplastic Elastomer

### Key Characteristics

#### Product Description

Versaflex™ CE 3180 is targeted for consumer electronics applications where excellent abrasion resistance, chemical resistance and silky feel are required.

Versaflex™ CE 3180 can also overmold to a variety of substrates including PC, ABS, PC/ABS, and Copolyester.

#### General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East	• Asia Pacific	• North America
Features	• Abrasion Resistant • Chemical Resistant • Good Colorability	• Good Processability • Low Friction • Pleasing Surface Appearance	• UV Resistant
Uses	• Appliances • Communication Applications • Computer Components • Consumer Applications	• Electrical/Electronic Applications • Flexible Grips • Overmolding • Soft Touch Applications	• Thick-walled Parts • Thin-walled Parts
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Natural Color	
Forms	• Pellets		
Processing Method	• Injection Molding		

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.17	1.17	ASTM D792
Molding Shrinkage - Flow (380°F (193°C))	6.0E-3 to 0.012 in/in	0.60 to 1.2 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress <sup>2, 3</sup> (300% Strain, 73°F (23°C))	1160 psi	8.00 MPa	ASTM D412
Tensile Strength <sup>2, 3</sup> (Break, 73°F (23°C))	2320 psi	16.0 MPa	ASTM D412
Tensile Elongation <sup>2, 3</sup> (Break, 73°F (23°C))	580 %	580 %	ASTM D412
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore A, 10 sec)	79	79	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity 392°F (200°C), 11200 sec <sup>-1</sup>	23.0 Pa·s	23.0 Pa·s	ASTM D3835
Additional Information	Typical Value (English)	Typical Value (SI)	Test Method
Mass Loss - 500 Cycle Abrasion Resistance <sup>4</sup> (73°F (23°C))	2.0 mg	2.0 mg	ASTM D3389

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Drying Temperature	125 to 140 °F	51.7 to 60.0 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Suggested Max Moisture	< 0.030 %	< 0.030 %
Suggested Max Regrind	20 %	20 %

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Injection	Typical Value (English)	Typical Value (SI)
Rear Temperature	340 to 360 °F	171 to 182 °C
Middle Temperature	360 to 410 °F	182 to 210 °C
Front Temperature	370 to 420 °F	188 to 216 °C
Nozzle Temperature	380 to 430 °F	193 to 221 °C
Processing (Melt) Temp	380 to 425 °F	193 to 218 °C
Mold Temperature	55.0 to 85.0 °F	12.8 to 29.4 °C
Back Pressure	0.00 to 50.0 psi	0.00 to 0.345 MPa
Screw Speed	50 to 100 rpm	50 to 100 rpm

**Injection Notes**

Typical colorant letdown ratios are 50:1 to 25:1 - loading levels should be as low as possible to minimize the effect on adhesion. A high color match consistency can be obtained by the use of precolored compounds available from GLS. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials. Contact GLS for more information on appropriate color concentrate base resins.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Versaflex™ CE 3180 should not be left in the barrel for extended idle periods (greater than 5 minutes).

Suggested Dewpoint: -40°F

Injection Speed: 0.5 to 2 in/sec

1st Stage - Boost Pressure: 500 to 1,000 psi

2nd Stage - Hold Pressure: 20-60% of Boost

Hold Time (Thick Part): 2 to 4 sec

Hold Time (Thin Part): 1 to 2 sec

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> Die C

<sup>3</sup> 2 hr

<sup>4</sup> Abrasion wheel: H-18  
Mass Lost

**CONTACT INFORMATION****Americas**

United States - Avon Lake  
+1 440 930 1000

United States - McHenry  
+1 815 385 8500

**Asia**

China - Guangzhou  
+86 20 8732 7260

China - Shenzhen  
+86 755 2969 2888

China - Suzhou  
+86 512 6823 24 38

China - Suzhou  
+86 512 6265 2600

Hong Kong -  
+852 2690 5332

Taiwan - Yonghe City,  
+886 9396 99740, +886 2929 1849

**Europe**

Germany - Gaggenau  
+49 7225 6802 0

Spain - Barbastro (Huesca)  
+34 974 310 314



*Beyond Polymers.*

*Better Business Solutions.™*

www.polyone.com

**PolyOne Americas**

33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE

**PolyOne Asia**

No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 201203, China  
+86 21 5080 1188

**PolyOne Europe**

6 Giällewee  
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.