



FireCon™ CPE 30-2 RoHS BLACK

Chlorinated Polyethylene

Key Characteristics

Product Description

CPE-30-2 RoHS BLACK is a RoHS compliant heavy duty thermoplastic jacket for power and control cables. It is suitable for VW1 and tray fire rated applications. CPE-30-2 RoHS BLACK has a good balance of low temperature, oil resistance and fire retardant properties.

General

Material Status	• Commercial: Active		
Regional Availability	• Asia Pacific	• Latin America	• North America
Uses	• Cable Jacketing	• Wire & Cable Applications	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	1.36	1.36	ASTM D792
Appearance	Pellets/Cubes	Pellets/Cubes	ASTM D2090
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	1000 psi	6.89 MPa	ASTM D638
Tensile Strength ² (Break)	1500 psi	10.3 MPa	ASTM D638
Tensile Elongation ² (Break)	350 %	350 %	ASTM D638
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore D, 10 sec)	35	35	ASTM D2240
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Brittleness Temperature	-31.0 °F	-35.0 °C	ASTM D746
Flammability	Typical Value (English)	Typical Value (SI)	Test Method
Oxygen Index (0.0750 in (1.91 mm))	32 %	32 %	ASTM D2863

Additional Information

Note: Pre-drying is recommended for 4 hours at 175°-185°F.

Note: Typical processing temperatures range between 320°-390°F depending upon screw design. Contact Technical Service for recommendation for specific equipment.

NOTE: Typical Properties of Molded Slab (0.075"); Not to be Construed as Specifications.

Notes

¹ Typical values are not to be construed as specifications.

² Type IV, 20 in/min (510 mm/min)

CONTACT INFORMATION**Americas**

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions. SM

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.