



KRATON® D2109 DS-N

Kraton Polymers LLC - Styrene Butadiene Styrene Block Copolymer

Wednesday, July 20, 2016

General Information

Product Description

Kraton D2109 DS-N is an easy processing, general purpose 45 Shore A hardness material designed for a wide variety of applications. It is supplied from North America in the physical form identified below.

- Kraton D2109 DS-N - supplied as a translucent dense pellet

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• General Purpose	• Good Processability	• Recyclable Material
Uses	• General Purpose		
Appearance	• Translucent		
Forms	• Pellets		
Processing Method	• Blow Molding • Coating	• Compression Molding • Extrusion	• Injection Molding

ASTM & ISO Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	0.917 to 0.947	0.917 to 0.947	Internal Method
Melt Mass-Flow Rate (MFR) (200°C/5.0 kg)	15 to 30 g/10 min	15 to 30 g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.025 to 0.027 in/in	2.5 to 2.7 %	ASTM D955
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ²			ASTM D412
Across Flow : 100% Strain	150 psi	1.03 MPa	
Flow : 100% Strain	150 psi	1.03 MPa	
Across Flow : 300% Strain	300 psi	2.07 MPa	
Flow : 300% Strain	300 psi	2.07 MPa	
Tensile Strength ²			ASTM D412
Across Flow : Yield	700 psi	4.83 MPa	
Flow : Yield	700 psi	4.83 MPa	
Tensile Elongation ²			ASTM D412
Across Flow : Break	550 %	550 %	
Flow : Break	550 %	550 %	
Tear Strength ²			ASTM D624
Across Flow	125 lbf/in	21.9 kN/m	
Flow	125 lbf/in	21.9 kN/m	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness			Internal Method
Shore A, 248°F (120°C), Compression Molded	40 to 50	40 to 50	

Copyright ©, 2016 PolyOne Distribution Company The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained therefrom. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. PolyOne Distribution Company shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond PolyOne Distribution Company's direct control. PolyOne Distribution Company MAKES NO WARRANTIES, EXPRESS OR IMPLIED, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendations, nor as an inducement to practice any patented invention without permission of the patent owner.

KRATON® D2109 DS-N

Kraton Polymers LLC - Styrene Butadiene Styrene Block Copolymer

Processing Information		
Injection	Typical Value (English)	Typical Value (SI)
Rear Temperature	340 to 360 °F	171 to 182 °C
Front Temperature	370 to 390 °F	188 to 199 °C
Nozzle Temperature	350 to 380 °F	177 to 193 °C
Mold Temperature	50.0 to 100 °F	10.0 to 37.8 °C
Injection Pressure	500 to 700 psi	3.45 to 4.83 MPa
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	40.0 to 60.0 psi	0.276 to 0.414 MPa

Notes

¹ Typical properties: these are not to be construed as specifications.

² Die C