



# Versaflex™ D2109 W

## Thermoplastic Elastomer

### Key Characteristics

Product Description	
Versaflex™ D2109 W is an easy processing, general purpose material designed for a wide variety of applications	
General	
Material Status	• Commercial: Active
Regional Availability	• Africa & Middle East • Europe • Asia Pacific • Latin America • North America
Agency Ratings	• FDA Unspecified Rating
RoHS Compliance	• RoHS Compliant
Appearance	• White
Forms	• Pellets
Processing Method	• Extrusion • Injection Molding

### Technical Properties <sup>1</sup>

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	0.930	0.930	ASTM D792
Molding Shrinkage			ISO 294-4
Across Flow	2.1 to 2.5 %	2.1 to 2.5 %	
Flow	2.2 to 2.8 %	2.2 to 2.8 %	
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tear Strength	130 lbf/in	22.8 kN/m	ASTM D624
Compression Set			ASTM D395
73°F (23°C), 22 hr	15 %	15 %	
158°F (70°C), 22 hr	90 %	90 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness <sup>2</sup>			ASTM D2240
Shore A, 10 sec, 73°F (23°C)	45	45	
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 11200 sec <sup>-1</sup>	21.5 Pa·s	21.5 Pa·s	

### Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Rear Temperature	310 to 380 °F	154 to 193 °C
Middle Temperature	320 to 390 °F	160 to 199 °C
Front Temperature	330 to 390 °F	166 to 199 °C
Nozzle Temperature	330 to 390 °F	166 to 199 °C
Mold Temperature	70 to 100 °F	21 to 38 °C
Injection Pressure	500 to 700 psi	3.45 to 4.83 MPa
Injection Rate	Moderate-Fast	Moderate-Fast
Back Pressure	50.0 to 150 psi	0.345 to 1.03 MPa
Screw Speed	25 to 75 rpm	25 to 75 rpm

Copyright © 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

**Injection Notes**

Color concentrates with ethylene vinyl acetate (EVA) carriers are most suitable for coloring Versaflex™ D2109 W. Improved color dispersion can be achieved by using higher melt flow concentrates (with a melt flow rate of 25 - 40 g/10 min). Typical loadings for color concentrates are 1% to 5% by weight. A high color match consistency may be obtained by using pre-colored compounds available from GLS. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polyethylene (PE) or polypropylene (PP).

Versaflex™ D2109 W has excellent melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

**Notes**

<sup>1</sup> Typical values are not to be construed as specifications.

<sup>2</sup> 2 hr

**CONTACT INFORMATION****Americas**

United States - Avon Lake  
+1 440 930 1000

United States - McHenry  
+1 815 385 8500

**Asia**

China - Guangzhou  
+86 20 8732 7260

China - Shenzhen  
+86 755 2969 2888

China - Suzhou  
+86 512 6823 24 38

China - Suzhou  
+86 512 6265 2600

Hong Kong -  
+852 2690 5332

Taiwan - Yonghe City,  
+886 9396 99740, +886 2929 1849

**Europe**

Germany - Gaggenau  
+49 7225 6802 0

Spain - Barbastro (Huesca)  
+34 974 310 314



*Beyond Polymers.*

*Better Business Solutions.™*

www.polyone.com

**PolyOne Americas**

33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000  
+1 866 POLYONE

**PolyOne Asia**

No. 88 Guoshoujing Road  
Z.J Hi-tech Park, Pudong  
Shanghai, 201203, China  
+86 21 5080 1188

**PolyOne Europe**

6 Giallewee  
+352 269 050 35

Copyright ©, 2016 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.