



Dynalloy™ OBC8000-T05

Thermoplastic Elastomer

Key Characteristics

Product Description

Dynalloy™ OBC8000-T05 is an ultra-soft TPE utilizing the unique rubber properties of Dows INFUSE™ Olefin Block Copolymers. This product is designed for injection molding applications where exceptional softness and overmolding to polypropylene is desired.

New Product. Commercial specifications have not been established.

- Adhesion to Polypropylene
- Enhanced Flow
- Excellent Colorability
- Tactile Feel
- Ultra Soft

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Colorability • Good Flow	• Good Processing Stability • Low Hardness	• Soft
Uses	• Consumer Applications • Flexible Grips	• Overmolding • Personal Care	• Seals • Transparent or Translucent Parts
Agency Ratings	• FDA 21 CFR 177.1210 ¹		
RoHS Compliance	• RoHS Compliant		
Appearance	• Translucent		
Forms	• Pellets		
Processing Method	• Injection Molding		

Technical Properties ²

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Specific Gravity	0.870	0.870	ASTM D792
Elastomers	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Stress ^{3, 4} (100% Strain, 73°F (23°C))	15.0 psi	0.103 MPa	ASTM D412
Tensile Stress ^{3, 4} (300% Strain, 73°F (23°C))	30.0 psi	0.207 MPa	ASTM D412
Tensile Strength ^{3, 4} (Break, 73°F (23°C))	182 psi	1.25 MPa	ASTM D412
Tensile Elongation ^{3, 4} (Break, 73°F (23°C))	1400 %	1400 %	ASTM D412
Compression Set			ASTM D395B
73°F (23°C), 22 hr	10 %	10 %	
104°F (40°C), 22 hr	19 %	19 %	
158°F (70°C), 22 hr	35 %	35 %	
Hardness	Typical Value (English)	Typical Value (SI)	Test Method
Durometer Hardness (Shore OO, 10 sec)	57	57	ASTM D2240
Fill Analysis	Typical Value (English)	Typical Value (SI)	Test Method
Apparent Viscosity			ASTM D3835
392°F (200°C), 1340 sec ⁻¹	40.0 Pa·s	40.0 Pa·s	
392°F (200°C), 11200 sec ⁻¹	7.60 Pa·s	7.60 Pa·s	

Copyright © 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Processing Information

Injection	Typical Value (English)	Typical Value (SI)
Suggested Max Regrind	20 %	20 %
Rear Temperature	300 to 340 °F	149 to 171 °C
Middle Temperature	330 to 370 °F	166 to 188 °C
Front Temperature	350 to 390 °F	177 to 199 °C
Nozzle Temperature	360 to 420 °F	182 to 216 °C
Processing (Melt) Temp	360 to 420 °F	182 to 216 °C
Mold Temperature	60.0 to 90.0 °F	15.6 to 32.2 °C
Back Pressure	0.00 to 80.0 psi	0.00 to 0.552 MPa
Screw Speed	80 to 120 rpm	80 to 120 rpm

Injection Notes

Color concentrates with Dynalloy™ OBC8000-T05 as the carrier are most suitable for coloring this product. If a OBC8000-T05 color concentrate carrier is desired, it is important that the chosen color house have underwater pelletization capabilities. Typical loadings for color concentrates are 1% to 5% by weight. Liquid color (pigment, not dye) can be used; white oil carriers are recommended. A high color match consistency can be obtained by using precolored compounds available from GLS. Polypropylene (PP) based color concentrates are not recommended because they lead to poor dispersion and can significantly change the hardness of the material. Concentrates based on PVC should not be used. The final determination of color concentrate suitability should be determined by customer trials.

Purge thoroughly before and after use of this product with a low flow (0.5 - 2.5 MFR) polystyrene (PS) or polypropylene (PP).

Regrind levels up to 20% can be used with Dynalloy™ OBC8000-T05 with minimal property loss, provided that the regrind is free of contamination. To minimize losses during molding, the melt temperature should remain as low as possible. The final determination of regrind effectiveness should be determined by the customer.

Dynalloy™ OBC8000-T05 has good melt stability. Maximum residence times may vary, depending on the size of the barrel. Generally, the barrel should be emptied if it is idle for periods of 8 - 10 minutes or longer.

Drying is not Required

Injection Speed: 0.5 to 3 in/sec

1st Stage - Boost Pressure: 200 to 700 psi

2nd Stage - Hold Pressure: 20% of Boost

Hold Time (Thick Part): 1 to 5 sec

Hold Time (Thin Part): 1 to 3 sec

Notes

¹ Please contact GLS Thermoplastic Elastomers for a copy of the FDA compliance letter.

² Typical values are not to be construed as specifications.

³ Die C

⁴ 2 hr

CONTACT INFORMATION

Americas

United States - Avon Lake
+1 440 930 1000

United States - McHenry
+1 815 385 8500

Asia

China - Guangzhou
+86 20 8732 7260

China - Shenzhen
+86 755 2969 2888

China - Suzhou
+86 512 6823 24 38

China - Suzhou
+86 512 6265 2600

Hong Kong -
+852 2690 5332

Taiwan - Yonghe City,
+886 9396 99740, +886 2929 1849

Europe

Germany - Gaggenau
+49 7225 6802 0

Spain - Barbastro (Huesca)
+34 974 310 314



Beyond Polymers.

Better Business Solutions.™

www.polyone.com

PolyOne Americas

33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000
+1 866 POLYONE

PolyOne Asia

No. 88 Guoshoujing Road
Z.J Hi-tech Park, Pudong
Shanghai, 201203, China
+86 21 5080 1188

PolyOne Europe

6 Giällewee
+352 269 050 35

Copyright ©, 2015 PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This data sheet shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.