



Edgetek™ AS-10GF/000 BLACK

Acrylonitrile Butadiene Styrene

Key Characteristics

Product Description

The Edgetek® Engineering Thermoplastic Compounds portfolio covers a broad range of standard and custom-formulated high performance materials. This portfolio includes high-temperature materials for elevated service temperature environments, high-modulus / structural materials for load-bearing and high-strength applications and flame-retardant products. These compounds are based on select engineering thermoplastic resins that are compounded with reinforcing additives such as carbon fiber, glass fiber and glass beads.

General

Material Status	• Commercial: Active		
Regional Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Features	• Amorphous	• Good Moldability	• Good Toughness
Uses	• Appliances • Automotive Applications	• Consumer Applications • General Purpose	• Industrial Applications • Structural Parts
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

Technical Properties ¹

Physical	Typical Value (English)	Typical Value (SI)	Test Method
Density / Specific Gravity	1.11	1.11	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	2.0E-3 to 4.0E-3 in/in	0.20 to 0.40 %	ASTM D955
Molding Shrinkage - Across Flow	7.5E-3 to 0.010 in/in	0.75 to 1.0 %	ASTM D955
Mechanical	Typical Value (English)	Typical Value (SI)	Test Method
Tensile Modulus ²	590000 psi	4070 MPa	ASTM D638
Tensile Strength ² (Break)	8500 psi	58.6 MPa	ASTM D638
Tensile Elongation ³ (Break)	2.0 to 3.0 %	2.0 to 3.0 %	ASTM D638
Flexural Modulus ⁴	570000 psi	3930 MPa	ASTM D790
Flexural Strength ⁴	13800 psi	95.1 MPa	ASTM D790
Impact	Typical Value (English)	Typical Value (SI)	Test Method
Notched Izod Impact	1.4 ft-lb/in	75 J/m	ASTM D256
Thermal	Typical Value (English)	Typical Value (SI)	Test Method
Deflection Temperature Under Load 66 psi (0.45 MPa), Unannealed	212 °F	100 °C	ASTM D648
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	194 °F	90.0 °C	ASTM D648

Notes

¹ Typical values are not to be construed as specifications.

² 0.20 in/min (5.1 mm/min)

³ Type I

⁴ 0.050 in/min (1.3 mm/min)